

VREX-0007USAAON00

CLAIMS

Please cancel claims 10, 11, 34, 35 and 51.

1. (Currently Amended) A method for creating a micropolarizer, comprising:
providing a first plate having a first and a second surface;
providing a second plate having a first and a second surface;
coating a polyimide on each of said first surface of said two plates;
exposing said first plate to linearly polarized UV light;
rubbing said polyimide coated upon said first surface of said first plate along a predetermined direction;
rubbing said polyimide coated upon said first surface of said second plate along a direction ~~having a predetermined angle in relation~~ perpendicular to said predetermined direction;
aligning said first plate and said second plate having said first surface of said first plate and said first surface of said second plate facing each other thereby creating a space there between; and
filling a liquid crystal between said space whereby a cell, or film is created.
2. (Original) The method of claim 1, further comprising:
using a mask having alternate transparent and opaque stripes coving said cell or film whereby a solidifying energy are being selectively applied there through; and
partially solidifying some portions said liquid crystal.
3. (Original) The method of claim 2, further comprising:
removing said mask; and
heating said cell or film to a temperature set point, whereby unsolidified liquid crystals covered by said opaque stripes are being transformed into a different phase.
4. (Original) The method of claim 1, further comprising:
re-solidifying uncured nematics into an isotropic phase.

VREX-0007USAAON00

5. (Canceled)
6. (Original) The method of claim 2, wherein:
said solidifying comprises applying an ultraviolet light.
7. (Original) The method of claim 1, wherein:
said space having a substantially equidistance between said first surface of said first plate and said first surface of said second plate.
8. (Original) The method of claim 1, wherein:
said liquid crystal comprises a nematic liquid crystal.
9. (Original) The method of claim 8, wherein:
said nematic liquid crystal comprises a type of polymerizable nematic liquid crystal.
10. (Canceled)
11. (Canceled)
12. (Original) The method of claim 1, wherein:
said two plates comprising flat glass plates.
13. (Canceled)
14. (Canceled)
15. (Canceled)
16. (Canceled)
17. (Canceled)

VREX-0007USAAON00

18. (Canceled)
19. (Canceled)
20. (Canceled)
21. (Canceled)
22. (Canceled)
23. (Canceled)
24. (Currently Amended) A method for creating a micropolarizer, comprising:
providing a first plate having a first and second surface;
coating a polyimide on said first surface of said first plate;
exposing said first plate with linearly polarized UV light;
rubbing said polyimide coated upon said first surface of said first plate along a
predetermined direction;
coating a photo resist on top of said polyimide;
patterning said photo resist into a predetermined alternatively spaced strips;
re-rubbing said polyimide coated upon said first surface of said first plate along a
direction ~~having a predetermined angle in relation~~ perpendicular to said predetermined
direction; and
rinsing off said photo resist.
25. (Original) The method of claim 24, further comprising:
providing a second plate having a first and a second surface;
coating a polyimide on said first surface of said first plate;
rubbing said polyimide coated upon said first surface of said first plate along a
predetermined direction;

VREX-0007USAAON00

aligning said first plate and said second plate having said first surface of said first plate and said first surface of said second plate facing each other thereby creating a space there between; and

filling a liquid crystal between said space whereby a cell, or film is created.

26. (Original) The method of claim 24, further comprising:
solidifying said liquid crystal.
27. (Canceled)
28. (Original) The method of claim 26, wherein:
said solidifying comprises applying an ultraviolet light.
29. (Original) The method of claim 24, further comprising:
re-solidifying uncured nematics into an isotropic phase.
30. (Original) The method of claim 29, wherein:
said solidifying comprises applying an ultraviolet light.
31. (Original) The method of claim 25, wherein:
said space having a substantially equidistance between said first surface of said first plate and said first surface of said second plate.
32. (Original) The method of claim 24, wherein:
said liquid crystal comprising a nematic liquid crystal.
33. (Original) The method of claim 32, wherein:
said nematic liquid crystal comprising a type of polymerizable nematic liquid crystal.
34. (Canceled)

VREX-0007USAAON00

35. (Canceled)

36. (Canceled)

37. (Canceled)

38. (Canceled)

39. (Canceled)

40. (Canceled)

41. (Canceled)

42. (Canceled)

43. (Canceled)

44. (Canceled)

45. (Canceled)

46. (Canceled)

VREX-0007USAAON00

47. (Canceled)

48. (Canceled)

49. (Canceled)

50. (Canceled)

51. (Canceled)